



T.R.  
SULEYMAN DEMIREL UNIVERSITY  
MINING ENGINEERING DEPARTMENT  
NATURAL STONE TECHNOLOGY LABORATORY  
32260 / ISPARTA/TURKEY

Phone: +90 246 211 1308 - 211 1305 - 211 1703 Fax: +90 246 237 0859

Gsm: (532) 408 4974 (538) 735 0209


E-mail: [servetdemirdag@sdu.edu.tr](mailto:servetdemirdag@sdu.edu.tr); [nazmisengun@sdu.edu.tr](mailto:nazmisengun@sdu.edu.tr)

Company Name : Efendioglu Marble Industry Trade Inc.  
Commercial Designation of Sample : Maroon Marinace

Date: 02 / 06 / 2015

| PHYSICAL AND MECHANICAL PROPERTIES                            |                                    |                      |                                     |              |             |
|---|------------------------------------|----------------------|-------------------------------------|--------------|-------------|
|   | Metric System                      |                      | SI System                           |              | Standard    |
| Hardness  | Mohs                               | 3.5-4                | Mohs                                | 3.5-4        | TS 6809     |
| Bulk Specific Gravity   |                                    |                      |                                     |              |             |
| Dry   | g/cm <sup>3</sup>                  | 2.699 ± 0.003        | kg/m <sup>3</sup>                   | 2699 ± 3     | TS EN 1936  |
| Saturated   | g/cm <sup>3</sup>                  | 2.701 ± 0.002        | kg/m <sup>3</sup>                   | 2701 ± 2     |             |
| Density   | g/cm <sup>3</sup>                  | 2.714 ± 0.005        | kg/m <sup>3</sup>                   | 2714 ± 5     | TS EN 1936  |
| Water Abs. at Atm. Press.                                     |                                    |                      |                                     |              |             |
| by Volume   | %                                  | 0.241 ± 0.06         | %                                   | 0.241 ± 0.06 | TS EN 13755 |
| by Weight   | %                                  | 0.089 ± 0.02         | %                                   | 0.089 ± 0.02 |             |
| Water Abs. at Boiling Water                                   |                                    |                      |                                     |              |             |
| by Volume   | %                                  | 0.288 ± 0.07         | %                                   | 0.288 ± 0.07 | TS 699      |
| by Weight   | %                                  | 0.107 ± 0.03         | %                                   | 0.107 ± 0.03 |             |
| Effective Porosity  | %                                  | 0.241                | %                                   | 0.241        | TS EN 1936  |
| Real Porosity   | %                                  | 0.55                 | %                                   | 0.55         | TS EN 1936  |
| Fullness Ratio  | %                                  | 99.45                | %                                   | 99.45        | TS 699      |
| Compressive Strength  | kg/cm <sup>2</sup>                 | 1406 ± 173           | MPa                                 | 137.9 ± 17.0 | TS EN 1926  |
| Compressive Strength after Freeze-Thaw (12 cyc.)              | kg/cm <sup>2</sup>                 | 1248 ± 192           | MPa                                 | 122.3 ± 18.8 | TS EN 12371 |
| Changing of Compressive Strength after Freeze-Thaw (-)        | %                                  | 11.27                | %                                   | 11.27        | TS EN 12371 |
| Decreasing of Weight after Freeze-Thaw                        | %                                  | 0.014                | %                                   | 0.014        | TS EN 12371 |
| Elasticity Modulus  | kg/cm <sup>2</sup>                 | 2.90x10 <sup>5</sup> | GPa                                 | 28.5         | TS 2030     |
| Flexural Strength Under Concentrated Load                     | kg/cm <sup>2</sup>                 | 139 ± 18             | MPa                                 | 13.6 ± 1.7   | TS EN 12372 |
| Changing of Flexural Strength after Freeze-Thaw (-) (12 cyc.) | kg/cm <sup>2</sup>                 | 131 ± 13             | MPa                                 | 12.9 ± 1.3   | TS EN 12371 |
| Changing of Flexural Strength after Freeze-Thaw (-)           | %                                  | 5.69                 | %                                   | 5.69         | TS EN 12371 |
| Flexural Strength Under Constant Moment                       | kg/cm <sup>2</sup>                 | 159 ± 23             | MPa                                 | 15.6 ± 2.3   | TS EN 13161 |
| Impact Strength   | kg.cm/cm <sup>3</sup>              | 6.0                  | kg.cm/cm <sup>3</sup>               | 6.0          | TS 699      |
| Abrasion Strength (Method-B/Bohne)                            | cm <sup>3</sup> /50cm <sup>2</sup> | 10.8 ± 0.3           | cm <sup>3</sup> /50 cm <sup>2</sup> | 10.8 ± 0.3   | TS EN 14157 |
| Tensile Strength (Brazilian)                                  | kg/cm <sup>2</sup>                 | 93 ± 16              | MPa                                 | 9.1 ± 1.5    | TS 7654     |
| P-Wave Velocity   | m/s                                | 6374 ± 96            | m/s                                 | 6374 ± 96    | TS EN 14579 |

| CHEMICAL ANALYSIS (TS EN 15309) | Al <sub>2</sub> O <sub>3</sub> | CaO   | Fe <sub>2</sub> O <sub>3</sub> | MgO  | Na <sub>2</sub> O | K <sub>2</sub> O | SiO <sub>2</sub> | SO <sub>3</sub> | LOI   |
|---------------------------------|--------------------------------|-------|--------------------------------|------|-------------------|------------------|------------------|-----------------|-------|
|                                 | 0.07                           | 55.39 | 0.05                           | 0.91 | 0.033             | 0.028            | 0.2              | 0.06            | 43.15 |



Assoc. Prof. Dr. Nazmi ŞENGÜN



Assoc. Prof. Dr. Servet DEMİRDAĞ



T.C.  
SÜLEYMAN DEMİREL ÜNİVERSİTESİ  
MADEN MÜHENDİSLİĞİ BÖLÜMÜ  
DOĞAL TAŞLAR TEKNOLOJİ LABORATUARI  
32260 / ISPARTA

Tel: (246) 211 1308 - 211 1305 - 211 1974 Faks: (246) 237 0859  
Gsm: (532) 408 4974 (538) 735 0209  
E-mail: servetdemirdag@sdu.edu.tr; nazmisengun@sdu.edu.tr

Firma Adı : Efendioğlu Mermer San. Tic. A.Ş.

Numunenin Ticari Adı : Maroon Marinace

Tarih : 02 / 06 / 2015

| FİZİKSEL VE MEKANİK ÖZELLİKLER                                 |                                    |                      |                                     |              |             |
|--|------------------------------------|----------------------|-------------------------------------|--------------|-------------|
|  | Metrik Sistem                      |                      | SI Sistemi                          |              | Standart    |
|  | Mohs                               | 3,5-4                | Mohs                                | 3,5-4        |             |
| Sertlik  |                                    |                      |                                     |              | TS 6809     |
| Birim Hacim Ağırlık  |                                    |                      |                                     |              |             |
| Kuru   | g/cm <sup>3</sup>                  | 2,699 ± 0,003        | kg/m <sup>3</sup>                   | 2699 ± 3     | TS EN 1936  |
| Doygun   | g/cm <sup>3</sup>                  | 2,701 ± 0,002        | kg/m <sup>3</sup>                   | 2701 ± 2     |             |
| Özgül Ağırlık  | g/cm <sup>3</sup>                  | 2,714 ± 0,005        | kg/m <sup>3</sup>                   | 2714 ± 5     | TS EN 1936  |
| Atmosfer Basıncında  |                                    |                      |                                     |              |             |
| Hacimce Su Emme  | %                                  | 0,241 ± 0,06         | %                                   | 0,241 ± 0,06 | TS EN 13755 |
| Ağırlıkça Su Emme  | %                                  | 0,089 ± 0,02         | %                                   | 0,089 ± 0,02 |             |
| Kaynar Suda  |                                    |                      |                                     |              |             |
| Hacimce Su Emme  | %                                  | 0,288 ± 0,07         | %                                   | 0,288 ± 0,07 | TS 699      |
| Ağırlıkça Su Emme  | %                                  | 0,107 ± 0,03         | %                                   | 0,107 ± 0,03 |             |
| Görünür Porozite   | %                                  | 0,241                | %                                   | 0,241        | TS EN 1936  |
| Gerçek Porozite  | %                                  | 0,55                 | %                                   | 0,55         | TS EN 1936  |
| Doluluk Oranı  | %                                  | 99,45                | %                                   | 99,45        | TS 699      |
| Basınç Dayanımı  | kg/cm <sup>2</sup>                 | 1406 ± 173           | MPa                                 | 137,9 ± 17,0 | TS EN 1926  |
| Don Sonrası Basınç Dayanımı<br>(12 Periyot)                    | kg/cm <sup>2</sup>                 | 1248 ± 192           | MPa                                 | 122,3 ± 18,8 | TS EN 12371 |
| Don Sonrası Basınç Dayanımı<br>Değişimi (-)                    | %                                  | 11,27                | %                                   | 11,27        | TS EN 12371 |
| Don Sonrası Kütle Kaybı  | %                                  | 0,014                | %                                   | 0,014        | TS EN 12371 |
| Elastisite Modülü  | kg/cm <sup>2</sup>                 | 2,90x10 <sup>5</sup> | GPa                                 | 28,5         | TS 2030     |
| Yoğun Yük Altında Bükülme<br>Dayanımı                          | kg/cm <sup>2</sup>                 | 139 ± 18             | MPa                                 | 13,6 ± 1,7   | TS EN 12372 |
| Don Sonrası Yoğun Yük Altında<br>Bükülme Dayanımı (12 Periyot) | kg/cm <sup>2</sup>                 | 131 ± 13             | MPa                                 | 12,9 ± 1,3   | TS EN 12371 |
| Don Sonrası Yoğun Yük Altında<br>Bükülme Dayanımı Değişimi (-) | %                                  | 5,69                 | %                                   | 5,69         | TS EN 12371 |
| Sabit Moment Altında Eğilme<br>Dayanımı                        | kg/cm <sup>2</sup>                 | 159 ± 23             | MPa                                 | 15,6 ± 2,3   | TS EN 13161 |
| Darbe Dayanımı   | kg.cm/cm <sup>3</sup>              | 6,0                  | kg.cm/cm <sup>3</sup>               | 6,0          | TS 699      |
| Aşınma Dayanımı<br>(Metod-B/Böhme)                             | cm <sup>3</sup> /50cm <sup>2</sup> | 10,8 ± 0,3           | cm <sup>3</sup> /50 cm <sup>2</sup> | 10,8 ± 0,3   | TS EN 14157 |
| Çekme Dayanımı (Brazilian)                                     | kg/cm <sup>2</sup>                 | 93 ± 16              | MPa                                 | 9,1 ± 1,5    | TS 7654     |
| P - Dalga Hızı   | m/s                                | 6374 ± 96            | m/s                                 | 6374 ± 96    | TS EN 14579 |

| KİMYASAL ANALİZ<br>(TS EN 15309) | Al <sub>2</sub> O <sub>3</sub> | CaO  | Fe <sub>2</sub> O <sub>3</sub> | MgO  | Na <sub>2</sub> O | K <sub>2</sub> O | SiO <sub>2</sub> | SO <sub>3</sub> | LOI  |
|----------------------------------|--------------------------------|------|--------------------------------|------|-------------------|------------------|------------------|-----------------|------|
|                                  |                                | 0,07 | 55,39                          | 0,05 | 0,91              | 0,033            | 0,028            | 0,2             | 0,06 |

Doç. Dr. Nazmi ŞENGÜN

Doç. Dr. Servet DEMİRDAĞ